

1. PRODUCT NAME

Stripe Aid™

2. MANUFACTURER

Neyra Industries, Inc.
10700 Evendale Drive
Cincinnati, Ohio 45241

Phone: 513-733-1000
Toll Free: 800-543-7077
Fax: 513-733-3989
Email: info@neyra.com
Website: www.neyra.com

- **Stops Fuzzy Edges:** The sharpest, cleanest line possible, especially on textured, color coated surfaces.
- **No Show:** Non-pigmented and non-glossy; won't show through when tape is removed.
- **Efficient:** Eliminates the need for painting tape with color coat.
- **Fast Drying:** Less lost time on the job.

3. PRODUCT DESCRIPTION

Stripe Aid is an acrylic latex-based coating that always requires Dynastripe be applied as a top coat.

Packaging:

Packaged in 1 gallon spouted jugs. 4 gallons per case.

Color:

As supplied, Stripe Aid is white, and dries to a clear, non-glossy film.

Basic Uses:

Stripe Aid is used to close the gap between a textured, colored pavement surface and the tape applied to the surface, assuring a straight line free of bleeding.

Composition:

As shipped, Stripe Aid is an acrylic emulsion.

Limitations:

In the liquid state, Stripe Aid must be protected from freezing and rain. Do not store in direct sunlight or where temperature exceeds 120°F.

4. INSTALLATION

Preparatory Work:

The surface must be structurally sound, surface cured and free from all loose or foreign matter prior to the application of Stripe Aid.

Methods:

Application of Stripe Aid may be by brush or roller. It is not necessary

to coat the entire width of the line, only the edges where the tape meets the surface.

Mix Design:

Do not thin under normal conditions. If necessary, thin with clean water at up to ½ pint per gallon. Over-thinning can result in insufficient solids to totally seal the tape edges.

Application:

For use over asphalt and concrete pavements, the following application procedures are recommended for best results:

Optimum coverage is approximately 800 to 1,000 feet of line per gallon. ½ gallon is normally sufficient for a standard doubles tennis court. For rough surfaces, a second coat may be necessary.

Application must be made when ambient and pavement temperatures are above 50°F. Good drying conditions are required during the subsequent 8 hours and no temperatures below 50°F should be anticipated for 48 hours. Night time application is not recommended. Lower temperatures, high humidity, clouds or shade, and lack of air movement retard cure.

Precautions:

Wet Dynaflex must be protected at all times from freezing. Keep out of reach of children. Container should be

closed when not in use. Avoid breathing vapor or contact with skin or eyes. Consult specific Neyra material safety data sheet before use.

New asphalt should be allowed to cure for a minimum of 15 days prior to application and must not exhibit ribboning, crawling, nor show oil rings when 1 gal. of clean water is poured onto the surface.

New concrete pavement should be allowed to cure for a minimum of 30 days prior to application.

5. MAINTENANCE

Proper care of the finished surface will maintain the attractive appearance and prolong the service of the Dynaflex coating system. Keeping leaves and other foreign matter off the surface and occasional flushing with clean cold water will achieve good results.

6. TECHNICAL DATA

Drying Time:

Allow to dry until clear and tack free.

Adhesion and Resistance to Water:

The cured coating exhibits no penetration, blistering, loss of adhesion, nor tendency to re-emulsify after immersion for 24 hours. Complete sampling and test procedures are available upon request.

Environmental Considerations:

Stripe Aid is considered non-hazardous when tested according to the EPA's TCLP (Toxicity Characteristic Leaching Procedure). Stripe Aid is a water-based material containing less than 73g/L (0.6 l lbs./gal.) VOC content.

7. TECHNICAL SERVICES

C.S.I. formatted application specifications, material safety data sheets, special project submittals, product and application recommendations as well as assistance with special situations and field service are available.

8. WARRANTY

The above specifications on product usage are believed to be true and accurate. Neyra Industries, Inc. guarantees that all materials manufactured comply with quality standards as described in the product data sheets. Because the application, handling, weather, workmanship and equipment are beyond the control of this manufacturer, only the quality of the products as shipped is guaranteed. In no case will the liability of Neyra Industries, Inc. exceed the purchase price of the shipped materials.

9. ADDITIONAL INFORMATION

Neyra Industries, Inc. manufactures a full line of recreational surface and asphalt pavement maintenance products as well as application equipment sold and distributed nationally at our plants and through distributors and contractors. To find the supplier most convenient to you, please contact us.

NEYRA

**Neyra Industries, Inc.
10700 Evendale Drive
Cincinnati, Ohio 45241**

Phone: 513-733-1000

Toll Free: 800-543-7077

Fax: 513-733-3989

Email: info@neyra.com

Website: www.neyra.com