

### 1. PRODUCT NAME Dynaflex® Acrylic Color Coating

### 2. MANUFACTURER

Neyra Industries, Inc.  
10700 Evendale Drive  
Cincinnati, Ohio 45241

Phone: 513-733-1000  
Toll Free: 800-543-7077  
Fax: 513-733-3989  
Email: info@neyra.com  
Website: www.neyra.com

- **Long Lasting:** Premium 100% acrylic polymer fortified with reinforcing pigments provide up to 50% greater wear.
- **Ease of Application:** Engineered for improved ease of use. Just add sand, water, mix and apply by squeegee or spray.
- **No Streaking:** Formulation provides uniform application and color over asphalt or concrete services.
- **Sand Suspension:** Excellent sand suspension during application provides uniform appearance and playing surface.
- **Non-Fading Colors:** Pure, high quality synthetic mineral oxide pigments are used for improved color stability for years of service.
- **LEED Green Building Compliant:** Custom colors can be formulated to meet "High Albedo Coatings" requirements.

### 3. PRODUCT DESCRIPTION

Dynaflex Acrylic Color Coating is a premium quality, highly pigmented, acrylic emulsion. The product is also formulated with a surfactant package which promotes superior adhesion to concrete or asphalt surfaces. Dynaflex contains no asbestos or mercury.

#### Packaging:

Packaged in 5 gal. pails and 55 gal. steel drums. 250 gal. totes are available as a special order.

#### Color:

Stock colors are beige, red, gray, tournament blue, sky blue, tournament green, light green and purple. Custom colors are also available.

#### Basic Uses:

Dynaflex provides long wearing, non-fading color and texture to asphalt and concrete pavements including tennis courts, basketball courts, playgrounds and walkways. For courts, mix designs can be adjusted to optimize speed of play and bounce requirements. Dynaflex in custom colors meets the LEED Green Building requirements.

#### Composition:

Dynaflex Acrylic Color Coating is a blend of binders, pigments, surfactants and rheological agents in a water based emulsion. Premium quality 100% acrylic polymers give Dynaflex its tough, long wearing character.

Pure, high grade synthetic mineral

oxide pigments that have been tested for color stability and resistance to ultraviolet light give Dynaflex its rich matte colors.

The surfactants blended into Dynaflex create a superior bond between the product and the pavement surface.

The rheological agents allow the emulsion to maintain long shelf life and an excellent non-settling character.

#### Limitations:

In the liquid state, Dynaflex must be protected from freezing and rain. Do not store in direct sunlight or where temperature exceeds 120°F.

### 4. INSTALLATION

#### Preparatory Work:

The surface must be structurally sound, surface cured and free from all loose or foreign matter prior to the application of Dynaflex.

An asphalt recreational surface should be checked for irregularities or depressions deeper than 1/8" (birdbaths). Fill to level of surrounding surface with hot mix asphalt or Dynabinder (Product Data Sheet 261) prior to the application of Dynaflex.

On a concrete recreational surface, the finish should be wood float or light broom, not steel troweled. The surface should be checked for depressions deeper than 1/8". Fill to level of

surrounding surface with Dynabinder Quick Patch Binder prior to the application of Dynaflex.

In addition, new concrete surfaces should be lightly abraded or lightly acid-etched and then primed with Dynabond Primer (Product Data Sheet 251) prior to the application of Dynaflex.

**Note:** In all cases a vapor barrier beneath concrete surface is strongly recommended.

#### Methods:

Dynaflex can be applied by squeegee, brush or spray. On new tennis or basketball courts, squeegee application is the recommended method.

#### Mix Design:

Dynaflex is a highly concentrated material intended to be mixed with water and mineral aggregate to form a ready to use color coating.

Per 55 gallons of Dynaflex

| Water      | Sand         | Yield       |
|------------|--------------|-------------|
| 22-28 gal. | 300-400 lbs. | 90-100 gal. |

All sand used should be clean, dry, pure silica sand, free of contaminants. Fine sand with an A.F.S. rating of 70 to 100 gives best results.

#### Application:

New construction of recreational surfaces often requires Dynaflex Acrylic

Resurfacer (Product Data Sheet 203) prior to color coating.

There is also the option of building up an acrylic cushion underlayment with Dynabond (Product Data Sheet 251), Sport-Mat (Product Data Sheet 210) and Sport-Top (Product Data Sheet 211) prior to color coating.

After the resurfacer or cushion underlayment has been given adequate time to dry thoroughly, Dynaflex texture color coats shall be applied by rubber-bladed squeegee in a minimum of two applications (a third color coat is optional). As a result, on a smooth sand or rubber textured surface, a properly mixed, ready-to-use material will cover at a rate of 10 to 20 sq. yds. per gallon.

Coverage rates can vary with the application method and the age, texture, and porosity of the pavement to be coated.

On recreational surfaces, the speed of play desired can be increased by one additional coat of Dynaflex Acrylic Color Coating diluted with water at the same rate as the Mix Design chart, but without the addition of silica sand.

Application must be made when ambient temperatures and pavement temperatures are above 50°F. Good drying conditions above 50°F are required during the subsequent 8 hours and no temperatures below 50°F should be anticipated for 48 hours. Night time application is not recommended. It is recommended that the area over which the application is made be opened to use only after trial shows it to be dried and sufficiently cured.

#### **Precautions:**

Liquid Dynaflex must be protected at all times from freezing. Keep out of reach of children. Container should be closed when not in use. Avoid breathing vapor or contact with skin or eyes. Consult specific Neyra material safety data sheet before use.

New asphalt should be allowed to cure for a minimum of 15 days prior to application and must not exhibit ribboning, crawling, nor show oil rings when 1 gal. of clean water is poured onto the surface.

New concrete pavement should be allowed to cure for a minimum of 30

days prior to application.

#### **5. MAINTENANCE**

Proper care of the finished surface will maintain the attractive appearance and prolong the service of the Dynaflex coating system. Keeping leaves and other foreign matter off the surface and occasional flushing with clean cold water will achieve good results.

#### **6. TECHNICAL DATA**

##### **Applicable Standards:**

Dynaflex in custom colors meets LEED-EB Heat Island Reduction: Non-Roof Option B Low Albedo Coatings. Dynaflex meets the composition and performance standards of ASTM D2833, "Architectural Paints and Coatings," when tested according to the following ASTM methods:

##### **Drying Time:**

When tested according to ASTM D1640, "set to touch" in 1 hour, dry to touch in 4 hours.

##### **Adhesion:**

When tested according to ASTM D3359 A, the dried film exhibits no loss of adhesion from the substrate.

##### **Flexibility:**

When tested according to ASTM D522 B, the dried film exhibits no loss of adhesion.

##### **Resistance to Water:**

When tested according to ASTM D870, the dried film exhibits no blistering, re-emulsification or color change.

##### **Flaking:**

When tested according to ASTM D662, the dried film exhibits no flaking.

##### **Cracking:**

When tested according to ASTM D661, the dried film exhibits no cracking or breaking.

##### **Chalking:**

When tested according to ASTM D4214, the dried film exhibits no chalking or friable powder development.

##### **Fading:**

When tested according to ASTM D4587, the dried film exhibits no fading

or color loss.

#### **Environmental Considerations:**

Dynaflex is non-hazardous when tested according to the EPA's TCLP (Toxicity Characteristic Leaching Procedure). Dynaflex is a water based material containing less than 142 g/L (1.22 lbs./gal.) VOC content.

#### **7. TECHNICAL SERVICES**

C.S.I. formatted application specifications, material safety data sheets, special project submittals, product and application recommendations as well as assistance with special situations and field service are available.

#### **8. WARRANTY**

The above specifications on product usage are believed to be true and accurate. Neyra Industries, Inc. guarantees that all materials manufactured comply with quality standards as described in the product data sheets. Because the application, handling, weather, workmanship and equipment are beyond the control of this manufacturer, only the quality of the products as shipped is guaranteed. In no case will the liability of Neyra Industries, Inc. exceed the purchase price of the shipped materials.

#### **9. ADDITIONAL INFORMATION**

Neyra Industries, Inc. manufactures a full line of recreational surface and asphalt pavement maintenance products as well as application equipment sold and distributed nationally at our plants and through distributors and contractors. To find the supplier most convenient to you, please contact us.

### **NEYRA**

**Neyra Industries, Inc.**

**10700 Evendale Drive**

**Cincinnati, Ohio 45241**

**Phone: 513-733-1000**

**Toll Free: 800-543-7077**

**Fax: 513-733-3989**

**Email: [info@neyra.com](mailto:info@neyra.com)**

**Website: [www.neyra.com](http://www.neyra.com)**